

CHANGZHOU JIASHUN NEW MATERIAL TECHNOLOGY CO.,LTD.

Technical Data Sheet

Item Name		E-glass fiberglass cloth	Test standard	JC/T170-2012
Temperature		17℃	relative humidity	53%
Test items		Standard value	Average value	Marks
Material		E-glass fiberglass fabric	E-glass fiberglass fabric	
Weave Type		Plain	Plain	
Warp tex		136	136	
Weft tex		136	136	
Width mm		1020	1020	
Thickness mm		0.2±0.02	0.190	
Mass per unit area (g/m²)		200±15	199	
Warp density (Count/cm)	Warp	8±1	8	
	Weft	7±1	7	
Breaking strength N/25mm	Warp	≥980	1100	
	Weft	≥735	992	
Moisture content(%)		≤0.3	0.08	
Oil content(%)		0.40~0.80	0.43	
Sizing agent type		Silane type	Silane type	
<u>Test conclusion:</u> Qualified.			Issued by:	
2023 年 03 月 09 日			 2023 年 03 月 15 日	