

COMPOSITE TOP MATERIALS CO.

Technical Data Sheet

Item Name		E-glass fiberglass cloth	Test standard	JC/T170-2012
Temperature		17℃	relative humidity	53%
Test items		Standard value	Average value	备注
Material		E-glassfiber	E-glassfiber	
Weave Type		plain weave	plain weave	
Warp tex		200	200	
Warp tex		200	200	
Width mm		1000	1020	
Mass per unit area (g/m ²)		300±20	290	
Warp density (Count/cm)	Warp	8±1	8	
	Weft	7±1	6.8	
Breaking strength N/25mm	Warp	300±100	350	
	Weft	300±100	300	
Moisture content(%)		≤0.3	0.07	
Oil content(%)		0.40~0.80	0.48	
Mass per unit area (g/m ²)		Silicone-modified	Silicone-modified	
Test conclusion: Qualified. 2024 年 01 月 31 日 				