

CERTIFICATE OF ANALYSIS

Denier/Filament : 20/3

Luster : Bonding Bright (BRA)

LOT No. : B232

Date : 2024.09.30

Items	Unit	Result	Specification	Remark
Denier	d	21.0	20.0±3.0	ASTM-D1907
Tenacity*	g/d	4.18	4.00±0.40	ASTM-D2256
Elongation at break*	%	65.4	62.0±15.0	"
Oil Pick Up***	%	1.15	Above 0.50	-
Melting Temperature	°C	95	85~100	

* Test Speed: 1300mm/min, Guage Length: 500mm(Textechno STATIMAT M)

** Evenness measured by KEI-80C tester(Feed speed 50m/min, Normal type)

***OPU(Oil Pick Up) estimated by Oxford NMR